NOTES:

1. SUBSTRATE: FUSED SILICA

2. COATING (APPLY ACROSS CLEAR APERTURE)

S1: 266nm HR Coating

R(ABS) > 99.5% @ 266nm @ 45° AOI

R(AVG) > 99.5% FROM 263-268nm @ 45° AOI


DAMAGE THRESHOLD


PULSED: 2.5 J/cm², 20ns, 20 Hz @ 266nm

CW: 1MW/cm² @ 266nm



4. ROHS COMPLIANT





FOR INFORMATION ONLY DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2
SHAPE	PLANO	PLANO
SURFACE QUALITY	20-10	20-10
CLEAR APERTURE	19.08 x 13.50	Ø13.50
SURFACE FLATNESS	λ/20	λ/20
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED

		G	Eamuna Optic	S®
THIRD ANGLE PROJECTION	HIRD ANGLE TITLE 15mm 1/20 WAVE, 266nm, HR CTD HYP, HT R FS PRISM		HT RA,	
ALL DIMS IN	mm	DWG NO	37643	SHEET 1 OF 1